

TECATOR 5013 natural - Stock Shapes

Chemical Designation

PAI (Polyamidimide)

Colour

yellow-brown opaque

Density

1.4 g/cm³

Main features

- good impact strength
- high pressure resistance
- very good electrical insulation
- stiff
- high creep resistance
- high strength
- good wear resistance
- good thermal stability

Target Industries

- electrical engineering
- precision engineering
- mechanical engineering
- vacuum technology
- aircraft and aerospace technology
- semiconductor technology
- automotive industry

Mechanical properties	parameter	value	unit	norm	comment
Modulus of elasticity (tensile test)	50 mm/min	3800	MPa	DIN EN ISO 527-2	1) (1) For tensile test: specimen type 1b
Tensile strength	50 mm/min	151	MPa	DIN EN ISO 527-2	
Tensile strength at yield	50 mm/min	151	MPa	DIN EN ISO 527-2	
Elongation at break	50 mm/min	21	%	DIN EN ISO 527-2	
Modulus of elasticity (flexural test)	2 mm/min, 10 N	3900	MPa	DIN EN ISO 178	
Notched impact strength (Charpy)	2 J	13.2	kJ/m ²	DIN EN ISO 179-1eA	
Ball indentation hardness		240	MPa	ISO 2039-1	
Thermal properties	parameter	value	unit	norm	comment
Glass transition temperature		280	°C	DIN 53765	1) (1) Found in public sources.
Melting temperature		n.a.	°C	DIN 53765	2) (2) n.a. = not applicable
Heat distortion temperature	1.82 MPa	278	°C	ASTM D 648	3) (3) Found in public sources. Individual testing regarding application conditions is mandatory.
Service temperature	short term	270	°C	-	3)
Service temperature	long term	250	°C	-	
Thermal expansion (CLTE)	23-55°C, long.	3.1	10 ⁻⁵ K ⁻¹	ASTM D 695	
Thermal conductivity		0.29	W/(K*m)	ASTM E1530	
Electrical properties	parameter	value	unit	norm	comment
Specific surface resistance		10 ¹⁸	Ω	ASTM D 257	1) (1) Found in public sources.
Specific volume resistance		10 ¹⁵	Ω*cm	ASTM D 257	2) (2) Found in public sources.
Dielectric strength		23	kV/mm	ASTM D 149	3) (3) Found in public sources.
Other properties	parameter	value	unit	norm	comment
Moisture absorption in normal climates	23°C, 50% rel. air humidity	2.5	%	DIN EN ISO 62	(1) Corresponding means no listing at UL (yellow card). The information might be taken from resin, stock shape or estimation. Individual testing regarding application conditions is mandatory.
Resistance to hot water/ bases		-	-	-	
Flammability (UL94)	corresponding to	V0		DIN IEC 60695-11-10;	1)

TECATOR has a high water uptake. Parts have to be pre-dried before fast heating to above 200 °C (drying process: 24 h per 3 mm wall thickness at 150 °C).

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at www.ensinger-online.com. Technical changes reserved.